



**AFRIMAT<sup>®</sup>**

<b>Name of Quarry:</b>	<b>Lyttelton Dolomite – Marble Hall</b>		
Town or City:	Marble Hall		
Telephone number:	013 261 1128		
Fax number:	013 261 1140		
Address:	Loskop North, JS12 Railway Street, Marble Hall		
Email:	stephan.becker@afrimat.co.za		
GPS Coordinates:	24°97'18" S	29°29'96" E	
Quarry Manager:	Stephan Becker	Cell number:	082 338 5328

Please indicate the material that your quarry manufactures or that you will be able to supply.

<b>Road Stone</b>	✓	<b>Concrete Stone</b>	✓	<b>Ballast</b>	✓
19 mm		53 mm		63 mm	
13,2 mm		37,5 mm		53 mm	
9,5 mm		26,5 mm			
6,7 mm		19 mm	✓		
4,75 mm		13,2 mm			
2-4 Grit		9,5 mm			
		6,7 mm			
		4,75 mm			
<b>Base</b>	✓	<b>Subbase</b>	✓	<b>Sand</b>	✓
G 1	✓	G 5	✓	Concrete Sand	✓
G 2		G 6		Plaster Sand	
G 3		G 7		Filling Sand	
G 4					
<b>Metallurgical Dolomite</b>	✓	<b>Agricultural</b>	✓	<b>Industrial Limestone</b>	✓
Sinter	✓	-1,7mm	✓	HCN Limestone	✓
63mm Lump	✓	2-4mm	✓	Amber Limestone	✓
SSD	✓				

Geological Deposit: (Type of material)	Limestone
Relative Density, %:	2.87
Water Absorption, %:	
Alkali Reactivity Expansion, %:	
Durability – Ethylene Glycol, %:	0.034
Polished Stone Value:	
Los Angeles Abrasion, %:	17.5
Silica Content, %:	

**Disclaimer**

The above data is based on continuous testing and is therefore regarded as average results and should not be used for calculation purposes. Please contact Afrimat technical services at johan.burger@afrimat.co.za or call 023 342 6026 for the latest up to date test results.