



**AFRIMAT**<sup>®</sup>

<b>Name of Quarry:</b>	<b>Gamohaam Quarry</b>		
Town or City:	Kuruman		
Telephone number:	082 807 2107		
Fax number:	086 236 8797		
Address:	Private Bag X1532, Suite 173, Kuruman, 8460		
Email:	willie.prins@afrimat.co.za		
GPS Coordinates:	27°22'17" S	23°17'16" E	
Quarry Manager:	Willie Prins	Cell number:	082 807 2107
Area Manager/Sales:	Willie Prins	Cell number:	082 807 2107

**Materials manufactured by this quarry:**

Road Stone	✓
19 mm	✓
13,2 mm	✓
9,5 mm	✓
6,7 mm	✓
4,75 mm	
2-4 Grit	

Concrete Stone	✓
53 mm	
37,5 mm	
26,5 mm	
19 mm	✓
13,2 mm	✓
9,5 mm	✓
6,7 mm	✓
4,75 mm	

Ballast	✓
63 mm	✓
53 mm	✓

Base	✓
G 1	✓
G 2	✓
G 3	✓
G 4	✓

Subbase	✓
G 5 – 53 mm	✓

Sand	✓
Concrete Sand	
Plaster Sand	
Filling Sand	

Other	✓	
Gabion	✓	+80 mm
Crusher Sand		-300 mm
Coarse Grit	✓	-10 mm
Fine Grit		-5 mm
Super Sand		-3 mm

Other	✓
Blasted Rock	
Overburden	
19 mm Crusher Run	✓
13 mm Crusher Run	

Geological Deposit: (Type of material)	Dolomite
Relative Density, %:	Loose 1.579    Compacted 1.625
Water Absorption, %:	0.2
Alkali Reactivity Expansion, %:	
Durability – Ethylene Glycol, %:	
Polished Stone Value:	48
Los Angeles Abrasion, %:	10.3
Silica Content, %:	

**Disclaimer**

The above data is based on continuous testing and is therefore regarded as average results and should not be used for calculation purposes. Please contact Afrimat technical services at johan.burger@afrimat.co.za or call 023 342 6026 for the latest up to date test results.