



AFRIMAT[®]

Name of Quarry:	Gamohaam Quarry		
Town or City:	Kuruman		
Telephone number:	082 807 2107		
Fax number:	086 236 8797		
Address:	Private Bag X1532, Suite 173, Kuruman, 8460		
Email:	michael.corbin@afrimat.co.za		
GPS Coordinates:	27°22'17" S	23°17'16" E	
Quarry Manager:	Willie Prins	Cell number:	082 807 2107
Area Manager/Sales:	Willie Prins	Cell number:	082 807 2107

Materials manufactured by this quarry:

Road Stone	✓
19 mm	✓
13,2 mm	✓
9,5 mm	✓
6,7 mm	✓
4,75 mm	
2-4 Grit	

Concrete Stone	✓
50 mm	
37,5 mm	
28 mm	
20 mm	✓
14 mm	✓
10 mm	✓
7,1 mm	✓
5 mm	

Ballast	✓
63 mm	✓
50 mm	✓

Base	✓
G 1	✓
G 2	✓
G 3	✓
G 4	✓

Subbase	✓
G 5 – 50 mm	✓

Sand	✓
Concrete Sand	
Plaster Sand	
Filling Sand	

Other	✓	
Gabion	✓	+80 mm
Crusher Sand		-300 mm
Coarse Grit	✓	-10 mm
Fine Grit		-5 mm
Super Sand		-3 mm

Other	✓
Blasted Rock	
Overburden	
20 mm Crusher Run	✓
14 mm Crusher Run	

Geological Deposit: (Type of material)	Dolomite
Relative Density, %:	Loose 1.579 Compacted 1.625
Water Absorption, %:	0.2
Alkali Reactivity Expansion, %:	
Durability – Ethylene Glycol, %:	
Polished Stone Value:	48
Los Angeles Abrasion, %:	10.3
Silica Content, %:	

Disclaimer

The above data is based on continuous testing and is therefore regarded as average results and should not be used for calculation purposes. Please contact Afrimat technical services at johan.burger@afrimat.co.za or call 023 342 6026 for the latest up to date test results.