



**AFRIMAT<sup>®</sup>**

<b>Name of Quarry:</b>	<b>Wolhuterskop Zuid</b>		
Town or City:	Bethlehem		
Telephone number:	058 303 5665/6		
Fax number:	058 303 5667		
Address:	Wolhuterskop Zuid, Stand 4038, Bethlehem, 9701		
Email:	charlotha.masut@afrimat.co.za		
GPS Coordinates:	28°26294" S	28°30308" E	
Quarry Manager:	Charlotha Masut	Cell number:	082 894 9232

Please indicate the material that your quarry manufactures or that you will be able to supply.

Road Stone	✓
20 mm	✓
14 mm	✓
10 mm	✓
7,1 mm	✓
5 mm	
2-4 Grit	

Concrete Stone	✓
50 mm	
37,5 mm	
28 mm	
20 mm	✓
14 mm	✓
10 mm	✓
7,1 mm	✓
5 mm	

Ballast	✓
63 mm	
50 mm	✓

Base	✓
G 1	✓
G 2	✓
G 3	
G 4	

Subase	✓
G 5	✓
G 6	
G 7	

Sand	✓
Concrete Sand	✓
Plaster Sand	
Filling Sand	

Other	✓
Gabion	✓
Riprap	
13,2 mm Gravseal	
Crusher Sand	✓
Slurry Dust	✓
Ralumac	
13,2 mm Drainage	
UTFC Stone	

Other	✓
Filling – 100 mm	
ROC with high PI	
UTFC Dust	
Dump Rock	✓

Geological Deposit: (Type of material)	
Relative Density, %:	2,94
Water Absorption, %:	0,4
Alkali Reactivity Expansion, %:	0,002
Durability – Ethylene Glycol, %:	0,27
Polished Stone Value:	52
Los Angeles Abrasion, %:	10,65
Silica Content, %:	0,69

**Disclaimer**

The above data is based on continuous testing and is therefore regarded as average results and should not be used for calculation purposes. Please contact Afrimat technical services at johan.burger@afrimat.co.za or call 023 342 6026 for the latest up to date test results.