



AFRIMAT[®]

Name of Quarry:	Lyttelton Dolomite		
Town or City:	Lyttelton, Centurion		
Telephone number:	012 664 5649		
Fax number:	012 664 5357		
Address:	Botha Avenue, Lyttelton, Centurion		
Email:	paul.botha@afrimat.co.za		
GPS Coordinates:	25°50'33.62" S	28°12'50.4" E	
Quarry Manager:	Piet Ackerman	Cell number:	082 338 5328

Please indicate the material that your quarry manufactures or that you will be able to supply.

Road Stone	✓	Concrete Stone	✓	Ballast	✓
19 mm		53 mm		63 mm	✓
13,2 mm		37,5 mm		53 mm	
9,5 mm		26,5 mm			
6,7 mm		19 mm	✓		
4,75 mm		13,2 mm			
2-4 Grit		9,5 mm	✓		
		6,7 mm			
		4,75 mm			
Base	✓	Subbase	✓	Sand	✓
G 1	✓	G 5	✓	Concrete Sand	
G 2		G 6	✓	Plaster Sand	
G 3		G 7	✓	Filling Sand	
G 4					
Other	✓	Other	✓		
Gabion	✓	Filling – 100 mm			
Riprap		ROC with high PI			
13,2 mm Gravseal		UTFC Dust			
Crusher Sand S/Sand	✓	Builders Blend	✓		
Slurry Dust		Unselected Dump Rock	✓		
Ralumac					
13,2 mm Drainage					
UTFC Stone					

Geological Deposit: (Type of material)	Dolomite
Relative Density, %:	2.87
Water Absorption, %:	0.23
Alkali Reactivity Expansion, %:	
Durability – Ethylene Glycol, %:	0.034
Polished Stone Value:	
Los Angeles Abrasion, %:	17.5
Silica Content, %:	

Disclaimer

The above data is based on continuous testing and is therefore regarded as average results and should not be used for calculation purposes. Please contact Afrimat technical services at johan.burger@afrimat.co.za or call 023 342 6026 for the latest up to date test results.