



AFRIMAT[®]

Name of Quarry:	Dundee		
Town or City:	Dundee		
Telephone Number:	034 218 1385		
Fax Number:	034 212 1237		
Address:	PO Box 1840, Dundee, 3000		
Email:	frans.chamberlain@afrimat.co.za		
GPS Coordinates:	28°08'50" S	30°11'35" E	
Quarry Manager:	Frans Chamberlain	Cell Number:	082 870 0139

Materials manufactured by this quarry:

Road Stone	✓
19 mm	✓
13,2 mm	✓
9,5 mm	✓
6,7 mm	
4,75 mm	
2-4 Grit	

Base	✓
G 1	
G 2	✓
G 3	
G 4	

Other	✓
Gabion	✓
Riprap	✓
13,2 mm Gravseal	
Crusher Dust	✓
Slurry Dust	✓
Ralumac	
13,2 mm Drainage	
UTFC Stone	

Concrete Stone	✓
53 mm	
37,5 mm	✓
26,5 mm	✓
19 mm	✓
13,2 mm	✓
9,5 mm	✓
6,7 mm	
4,75 mm	

Subase	✓
G 5	✓
G 6	
G 7	

Other	✓
Filling – 100 mm	
ROC with high PI	
UTFC Dust	

Ballast	✓
63 mm	
53 mm	

Sand	✓
Concrete Sand	
Plaster Sand	
Filling Sand	

Geological Deposit: (Type of material)	Dolerite
Relative Density, %:	2,93
Water Absorption, %:	0,4
Alkali Reactivity Expansion, %:	0,12
Durability – Ethylene Glycol, %:	0,225
Polished Stone Value:	53
ACV (Dry), %:	12,3
Crystalline Quartz, %:	1,06

Disclaimer

The above data is based on continuous testing and is therefore regarded as average results and should not be used for calculation purposes. Please contact Afrimat technical services at johan.burger@afrimat.co.za or call 023 342 6026 for the latest up to date test results.