



AFRIMAT[®]

Name of Quarry:	Friersdale Quarry		
Town or City:	Keimoes		
Telephone number:	054 463 0018		
Fax number:			
Address:			
Email:	michael.corbin@afrimat.co.za		
GPS Coordinates:	28°45'58" S	20°48'58" E	
Quarry Manager:	Willie Prins	Cell number:	082 807 2107

Please indicate the material that your quarry manufactures or that you will be able to supply.

Road Stone	✓
19 mm	✓
13,2 mm	✓
9,5 mm	✓
6,7 mm	✓
4,75 mm	
2-4 Grit	

Concrete Stone	✓
53 mm	
37,5 mm	
26,5 mm	
19 mm	✓
13,2 mm	✓
9,5 mm	✓
6,7 mm	✓
4,75 mm	

Ballast	✓
63 mm	✓
53 mm	✓

Base	✓
G 1	✓
G 2	
G 3	
G 4	✓

Subase	✓
G 5	✓
G 6	
G 7	

Sand	✓
Concrete Sand	
Plaster Sand	
Filling Sand	

Other	✓
Gabion	✓
Riprap	
13.2 mm Gravseal	
Crusher Sand	✓
Slurry Dust	✓
Ralumac	
13.2 mm Drainage	
UTFC Stone	

Other	✓
Filling – 100 mm	
ROC with high PI	
UTFC Dust	

Geological Deposit: (Type of material)	Dolorite
Relative Density, %:	2.60 – 2.70
Water Absorption, %:	0.1
Alkali Reactivity Expansion, %:	0.067
Durability – Ethylene Glycol, %:	Class 1
Polished Stone Value:	48
Los Angeles Abrasion, %:	
Silica Content, %:	68.5

Disclaimer

The above data is based on continuous testing and is therefore regarded as average results and should not be used for calculation purposes. Please contact Afrimat technical services at johan.burger@afrimat.co.za or call 023 342 6026 for the latest up to date test results.