



AFRIMAT[®]

Name of Quarry:	Hluhluwe		
Town or City:	Hluhluwe		
Telephone Number:	035 562 0831		
Fax Number:	035 562 0831		
Address:	PO Box 86, Hluhluwe, 3960		
Email:	marius.kruger@afrimat.co.za		
GPS Coordinates:	27°55'18" S	32°12'53.3" E	
Quarry Manager:	Marius Kruger	Cell Number:	082 899 4989

Materials manufactured by this quarry:

Road Stone	✓
19 mm	✓
13,2 mm	✓
9,5 mm	✓
6,7 mm	✓
4,75 mm	
2-4 Grit	

Concrete Stone	✓
53 mm	
37,5 mm	
26,5 mm	✓
19 mm	✓
13,2 mm	✓
9,5 mm	✓
6,7 mm	✓
4,75 mm	

Ballast	✓
63 mm	✓
53 mm	

Base	✓
G 1	
G 2	✓
G 3	
G 4	✓

Subase	✓
G 5	✓
G 6	✓
G 7	✓

Sand	✓
Concrete Sand	
Plaster Sand	
Filling Sand	

Other	✓
Gabion	✓
Riprap	✓
13,2 mm Gravseal	
Crusher Dust	✓
Slurry Dust	✓
Ralumac	
13,2 mm Drainage	
UTFC Stone	

Other	✓
Filling – 100 mm	
ROC with high PI	
UTFC Dust	

Geological Deposit: (Type of material)	Basalt
Relative Density, %:	
Water Absorption, %:	0,53
Alkali Reactivity Expansion, %:	0,03
Durability – Ethylene Glycol, %:	4,5
Polished Stone Value:	54
ACV (Dry), %:	14,4
Crystalline Quartz, %:	1,29

Disclaimer

The above data is based on continuous testing and is therefore regarded as average results and should not be used for calculation purposes. Please contact Afrimat technical services at johan.burger@afrimat.co.za or call 023 342 6026 for the latest up to date test results.