



AFRIMAT[®]

Name of Quarry:	Ladysmith		
Town or City:	Ladysmith, KZN		
Telephone Number:	081 250 2632		
Fax Number:	081 250 2632		
Address:	Rietfontein, Portion 8 of Portion 3, Ladysmith, KZN		
Email:	marius.theron@afrimat.co.za		
GPS Coordinates:	28°30'00" S	27°50'30" E	
Quarry Manager:	Marius Theron	Cell Number:	082 872 0925

Materials manufactured by this quarry:

Road Stone	✓
19 mm	
13,2 mm	
9,5 mm	
6,7 mm	
4,75 mm	
2-4 Grit	

Base	✓
G 1	
G 2	✓
G 3	
G 4	

Other	✓
Gabion	✓
Riprap	✓
13,2 mm Gravseal	
Crusher Sand	✓
Slurry Dust	✓
Ralumac	
13,2 mm Drainage	
UTFC Stone	

Concrete Stone	✓
53 mm	
37,5 mm	
26,5 mm	
19 mm	✓
13,2 mm	✓
9,5 mm	✓
6,7 mm	
4,75 mm	

Subase	✓
G 5	✓
G 6	
G 7	✓

Other	✓
Filling – 100 mm	
ROC with high PI	
UTFC Dust	
Kerbmix	

Ballast	✓
63 mm	✓
53 mm	

Sand	✓
Concrete Sand	
Plaster Sand	
Filling Sand	

Geological Deposit: (Type of material)	Dolorite
Relative Density, %:	2,95
Water Absorption, %:	0,4
Alkali Reactivity Expansion, %:	0,013
Durability – Ethylene Glycol, %:	0,03
Polished Stone Value:	52
Los Angeles abrasion, %:	7,9
Silica content, %:	1,06

Disclaimer

The above data is based on continuous testing and is therefore regarded as average results and should not be used for calculation purposes. Please contact Afrimat technical services at johan.burger@afrimat.co.za or call 023 342 6026 for the latest up to date test results.