



AFRIMAT[®]

Name of Quarry:	Qwa Qwa		
Town or City:	Qwa Qwa		
Telephone Number:	058 623 2861		
Fax Number:	058 622 3451		
Address:	PO Box 584, Harrismith, 9880		
Email:	anton.marnewick@afrimat.co.za		
GPS Coordinates:	28°25'0" S	28°53'0" E	
Quarry Manager:	Anton Marnewick	Cell Number:	082 655 8594

Materials manufactured by this quarry:

Road Stone	✓
19 mm	✓
13,2 mm	✓
9,5 mm	✓
6,7 mm	✓
4,75 mm	
2-4 Grit	

Base	✓
G 1	✓
G 2	✓
G 3	
G 4	✓

Other	✓
Gabion	✓
Riprap	✓
13,2 mm Gravseal	
Crusher Dust	✓
Slurry Dust	✓
Ralumac	
13,2 mm Drainage	
UTFC Stone	

Concrete Stone	✓
53 mm	
37,5 mm	
26,5 mm	✓
19 mm	✓
13,2 mm	✓
9,5 mm	✓
6,7 mm	✓
4,75 mm	

Subase	✓
G 5	✓
G 6	✓
G 7	✓

Other	✓
Filling – 100 mm	
ROC with high PI	
UTFC Dust	

Ballast	✓
63 mm	
53 mm	

Sand	✓
Concrete Sand	
Plaster Sand	
Filling Sand	

Geological Deposit: (Type of material)	Dolerite
Relative Density, %:	2,95
Water Absorption, %:	0,89
Alkali Reactivity Expansion, %:	0,14
Durability – Ethylene Glycol, %:	4,9
Polished Stone Value:	51
ACV (Dry), %:	12
Crystalline Quartz, %:	0,69

Disclaimer

The above data is based on continuous testing and is therefore regarded as average results and should not be used for calculation purposes. Please contact Afrimat technical services at johan.burger@afrimat.co.za or call 023 342 6026 for the latest up to date test results.